

GUIDE FORMULATIONS

Decorative Cement Plaster

<u>INGREDIENTS</u>	<u>AMOUNT (kg)</u>
PORTLAND CEMENT	110.00
VARIOUS FILLERS	824.00
LIME	55.00
STARCH ETER	0.2
POWDER SILICON	5.0
AIR ENTRAINING AGENTS	0.75
ANTIFOAM	0.25
CELOCELL HPMC	2
REDIPOL RDP 04	3

Coloring: If it's preferred, it can be added some iron oxide pigment.

Coloring: The cementer putty should be applied to the surface. Then, the plaster prepared upon above formulation should be applied to the surface with 5 mm thickness.

Warning: The information contained in this document is given in good faith and based on our current knowledge. There can be some further changes or amendments according to mixer type, applicators' preferences, testing aims. It's recommended to make trial production to get more accurate results. It is only an indication and is in no way binding, particularly as regards of infringement or prejudice to third parties through the use of our products.