

GUIDE FORMULATIONS

Granite Adhesive

<u>INGREDIENTS</u>	<u>AMOUNT (kg)</u>
PORTLAND CEMENT 42.5	25.00
PUZZOLANIC CEMENT	12.00
HYDRAULIC BINDER	3.0
QUARTZ SAND (0.1-0.6 mm)	50.00
GYPSUM	8.00
CALCIUM FORMATE	0.2
REDIPOL RDP04	1.50
CELOCELL PM20H/PM30H	0.30

Warning: The information contained in this document is given in good faith and based on our current knowledge. There can be some further changes or amendments according to mixer type, applicators' preferences, testing aims. It's recommended to make trial production to get more accurate results. It is only an indication and is in no way binding, particularly as regards of infringement or prejudice to third parties through the use of our products.