

GUIDE FORMULATIONS

Gypsum Plaster

<u>INGREDIENTS</u>	<u>AMOUNT (kg)</u>
GYPSUM	45.00
CALCIUM CARBONATE 0 - 1 mm	49.00
LIME	5.00
PERLITE	1.00
TARTARIC ACID	0.08
AIR ENTRAINING AGENTS	0.02
CELOCELL PM40H/PM60H	0.18 - 0.22
WATER	% 60 - 65

Warning: The information contained in this document is given in good faith and based on our current knowledge. There can be some further changes or amendments according to mixer type, applicators' preferences, testing aims. It's recommended to make trial production to get more accurate results. It is only an indication and is in no way binding, particularly as regards of infringement or prejudice to third parties through the use of our products.