

Celocell 1H

Hydroxyethylcellulose – HEC

Technical Data Sheet

CHARACTERISTICS: Celocell 1H, hydroxyethylcellulose gives powerful, stable thickening in both interior and exterior paints. A creamy in-can stability, excellent water resistance and a good rheology profile. At the same time, it serves as a protective colloid in emulsion polymerization.

TYPICAL PROPERTIES

Molar Substitution Degree		1,8 ~ 2,0
Loss on Drying (%)	MAX	10
Water Insoluble Matter (%)	MAX	0,5
Viscosity (mPa.s) 2% , 20 °C aqueous solution		700 - 1000
Residue on ignition (%)	MAX	5
Suspending pH Value		6,0 - 8,5

PHYSICAL PROPERTIES

Apperance	white or yellowish mobile powder
40 screen past rate (%)	≥99
Intenerating point (°C)	135 - 140
Vision density (lg/ml)	0.35 ~ 0.61
Dispersing point (°C)	205 ~ 210
Average moisture at 23°C (%)	6

PACKAGING: 25 Kg's multi layer paper

STORAGE: Store in it cool and dry place.

Warning: The information contained in this document is given in good faith and based on our current knowledge. It is only an indication and is in no way binding, particularly as regards of infringement or prejudice to third parties through the use of our products. We guarantee that our products comply with its sales specifications.